

**TEST CERTIFICATE**

**Date** : 28<sup>th</sup> October 2014.  
**Client** : Stage-Electrics Partnerships Ltd. (Flamecheck Plus).  
**Address** : Encore House, Unit 3 Britannia Rd, Patchway Trading Estate, Patchway, Bristol, BS34 5TA.  
**Date Recd.** : September 2014.  
**Test Date** : 03<sup>rd</sup> October 2014.  
**Order Number** : 296386.  
**Quotation Number:** Q144284.  
**Client Ref** : Polycotton mix 50/50

Test required : Flammability BS 5867-2: type B: 2008  
 Pre-treatment : None  
 Conditioning : A minimum of 24 hours at 20+/-2 Deg C and 65+/-5%RH  
 Method of test : BS EN ISO 15025: 2002 Procedure A (Surface ignition)  
 Flame application : 15 seconds using propane gas  
 Note: This certificate relate only to the material supplied and tested

Issue 2 this issue replaces the original issue in its entirety  
 Change: Client name change

Tested on face of fabric	Fabric length direction			Fabric width direction		
Specimen number	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge (✓ or x)	x	x	x	x	x	x
Hole reached an edge (✓ or x)	x	x	x	x	x	x
Flaming debris (✓ or x)	x	x	x	x	x	x

✓ = Yes it does burn to the edge or debris is flaming

X = No it does not burn to the edge or debris is not flaming

On the basis of these tests:

The above sample CONFORMS to the Flammability requirements of BS 5867-2: 2008 Type B.

In accordance with the requirements of BS5867 the fabric should be labelled

**"IF WETTED IN ANY WAY IT IS ESSENTIAL TO RE-TREAT THE FABRIC TO MEET FLAMMABILITY REQUIREMENTS"**.

End of Certificate.

Signature:

K.D.James

Technical Manager, for and on behalf of J.C.S. Technology

**Quality Management System Approved to ISO 9001:2008**

AJA Registrars Reg No 059-A Certificate Number AJA05/8373